# **Technical Datasheet**

version 23.12

## **PETG**

Nobufil PETG is a sustainable PETG made from recycled industrial waste sourced in Europe. We took great care to create a consistent high-quality material for you to enjoy. This material is suitable to print technical parts using FDM technology.

#### **Material properties**

Properties	FDM H	Injection		Method
Tensile strength	48	50	MPa	ISO 527
Elongation at break	8	4,5	%	ISO 527
Flexural strength		44	МРа	ISO 178
Flexural modulus		2150	МРа	ISO 178
Izod Impact strength notched	3	3,5	kJ/m²	ISO 180
Izod Impact strength unnotched	22	134	kJ/m²	ISO 180
HDT A		61	°C	ISO 75
Density		1,27	g/cm³	ISO 1183

### **Print settings**

235°C ± 10
75°C ± 10
textured PEI sheet
20-50%

## Storage and drying

Store between 18 to 25 °C in a dry area away from sunlight. Keep sealed in an airtight container away from humidity. Pre-dry material for 3-6 hours at 60°C (max.).

## Carbon footprint

This product is made from recycled plastic – approx. 60% of CO2 equivalents can be saved compared to raw materials from primary production.

#### Disclaimer

Although accurate, the data provided is not binding and do not constitute a formal warranty. It is supplied as a guide for costumers regarding the correct use of product.